Timzo Tufting Industry bv
P.O. Box 7, 8280 AA
Nijverheidstraat 27, 8281 JD
Genemuiden, The Netherlands

T (+31) 38 385 44 77
F (+31) 38 385 65 71
E carpets@timzo.nl
W www.condor-group.eu

NEVADA

Manufacturing process	Tufted		ISO 2424
Gauge	1/10" Loop		
Pilecomposition	100% PP		ISO 2424
Primary backing	Woven PP		ISO 2424
Secondary backing	Felt		ISO 2424
Width	400 cm	± 1%	EN 986
Pile weight	approx. 550 gr/m²		ISO 8543
Total weight	Felt : approx. 1704 gr/m²	± 15%	ISO 8543
Pile height	approx. 5,0 mm		ISO 1765
Total height	Felt : approx. 7,3 mm	+ 15% / -10%	ISO 1765
Number of knots	approx. 157.900 /m²	+ 10% / -7,5%	ISO 1763
Fire classification	Felt : Efl (EN13501-1)		EN 13501-1
Light fastness	≥ 5		105-B02
Wearability	≥ 4,5		105-X12
Water fastness	≥ 4,5		105-E01
Thermal resistance	0,120 m² K/W		ISO 8302
Sound isulation	10,0 dB		ISO 10140
GUT Nr.	Felt : D165EE7E		

Floorsymbols Felt

Certificates

EN 14041
22

Reaction to fire:
Efl (EN13501-1)

Slip resistance:
DS
Felt
DOP: 1058-128866

Textile Floorcovering
EN1307